
PLA PLUS
Datasheet



Density
1,24 g/cm^3 (23°C)

Melting point
160°C

Decomposition temperature
230°C

Recommended printing temperartue
200±10°C

Distortion temperature
70°C

Speed
6mm/min

Elongation
145%

Tolerance
1,75±0,03 / 3,00±0,05

First layer temperature
200°C

Heatbed temperature
60°C

Pack dimensions
235 x 215 x 80 mm

Pack weight
1,45 kg approx.

PLA, Polylactic Acid, is a biodegradable thermoplastic polymer obtained from corn starch, potato, yucca or sugar cane.

It is by far the most used material in FDM 3D printing. This material has evolved considerably from its beginnings to the material we have today, an easy-to-use filament capable of covering most of our needs.



- **The heatbed is optional**
- **It requires the use of laquer on the printing surface**

Products & Solutions globcl company

Saturn, 33
08228 Terrassa
Barcelona, Spain

Tel: (+34) 930027951
3dcpi@3dcpi.com
www.3dcpi.com