PETG HT 100
Datasheet

Density
1,27 g/cm^3 (23°C)

Melting point
-

Heatbed temperature
60°C-80°C

Recommended printing temperartue
230±10°C

Distortion temperature
110°C

Speed
40-120 mm/s

Elongation
150%

Tolerance
1,75±0,03 / 3,00±0,05

Tensile strength
44,1 MPa

Bending strength
87 MPa

Pack dimensions
235 x 215 x 80 mm

Pack weight
1,45 kg approx.

Flexural modulus
2180 MPa

Impact resistance
-

PETG 110 has the characteristics of PETG, reinforcing one of its shortcomings: resistance to temperature.

With the PETG 110 you can make very resistant pieces with a working temperature of 110 ° C.



- **The heatbed is required**
- **It requires the use of laquer on the printing surface**

Products & Solutions
globcl company

Saturn, 33
08228 Terrassa
Barcelona, Spain

Tel: (+34) 930027951
3dcpi@3dcpi.com
www.3dcpi.com