
PLA BRONZE

Datasheet



Density
1,50 g/cm³ (23°C)

Melting point
160°C

Decomposition temperature
190°C-240°C

Recommended printing temperartue
200±10°C

Distortion temperature
70°C

Speed
-

Elongation
145%

Tolerance
1,75±0,03 / 3,00±0,05

First layer temperature
-

Heatbed temperature
-

Pack dimensions
235 x 215 x 80 mm

Pack weight
1,45 kg approx.

Melt index
-

Impact resistance
-

With our attractive metallic bronze color we ensure that your pieces will not be in third place.

With this material you will get all the features of our PLA PLUS but with metallic and shiny finishes.

PLA, polylactic acid, is a biodegradable thermoplastic polymer obtained from corn starch, potato, yucca or sugar cane. It is by far the most used material in FDM 3D printing.



- **The heatbed is optional**
- **It requires the use of laquer on the printing surface**

Products & Solutions globcl company

Saturn, 33
08228 Terrassa
Barcelona, Spain

Tel: (+34) 930027951
3dcpi@3dcpi.com
www.3dcpi.com