PLA WOODEN
Datasheet

Density
0,93 g/cm^3 (23°C)

Melting point
160°C

Decomposition temperature
270°C

Recommended printing temperartue
210±10°C

Distortion temperature
80°C

Speed
40-120 mm/s

Elongation
40%

Tolerance
1,75±0,03 / 3,00±0,05

First layer temperature
220°C

Heatbed temperature
50°C

Pack dimensions
235 x 215 x 80 mm

Pack weight
1,45 kg approx.

Melt index
-

Impact resistance
-

Your pieces will look as natural as wood!

One of the characteristics of PLA is that it can be used as a binding polymer to which wood fibers are added, resulting in this material that will give it a finish similar to wood.

This filament contains 40% of recycled wood.



- **The heatbed is optional**
- **It requires the use of laquer on the printing surface**

Products & Solutions
globcl company

Saturn, 33
08228 Terrassa
Barcelona, Spain

Tel: (+34) 930027951
3dcpi@3dcpi.com
www.3dcpi.com